

ARMY RESEARCH LABORATORY



Thermophysical Properties of Six Solid Gun Propellants

by Martin S. Miller

ARL-TR-1322

March 1997

19970321 085

DTIC QUALITY INSPECTED 3

Approved for public release; distribution is unlimited.

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer need. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1322

March 1997

Thermophysical Properties of Six Solid Gun Propellants

Martin S. Miller

Weapons and Materials Research Directorate, ARL

DTIC QUALITY INSPECTED 3

Approved for public release; distribution is unlimited.

Abstract

Measurements are reported of the thermal conductivities and thermal diffusivities of six U.S. Army solid gun propellants over the temperature range -20C to +50C at atmospheric pressure. The propellants are members of the BRL research series propellants that have been widely distributed to research laboratories in the U.S. These propellants include representative types from each class of materials that are either in the fielded inventory or experimental ("X" prefix), i.e., a single base (M10), a double base (M9), a homogeneous triple base (JA2), a composite triple base (M30), a composite nitramine with inert plasticizer (XM39), and a composite nitramine with energetic plasticizer (M43). Conductivities and diffusivities were measured simultaneously using a new experimental technique developed specifically for the purpose. The experiment is designed to approximate the mathematical idealization of a one-dimensional, infinite, two-component, composite solid whose planar interface is subjected to a step-function heat flux. The average values obtained are estimated to be accurate to within $\pm 5\%$, and least-squares polynomial fits are provided for convenient use of the data in calculations. For convenience, a table is given summarizing the polynomial fits from the present measurements and from previous measurements of the specific heats for the same propellant lots.

TABLE OF CONTENTS

| | <u>Page</u> |
|----------------------------------|-------------|
| LIST OF FIGURES | iv |
| LIST OF TABLES | v |
| 1. INTRODUCTION | 1 |
| 2. EXPERIMENTAL TECHNIQUE | 2 |
| 3. PROPELLANT DESCRIPTIONS | 4 |
| 4. RESULTS | 8 |
| 5. CONCLUSIONS | 15 |
| 6. REFERENCES | 17 |
| DISTRIBUTION LIST | 19 |
| REPORT DOCUMENTATION PAGE | 25 |

INTENTIONALLY LEFT BLANK.

LIST OF FIGURES

| <u>Figure</u> | <u>Page</u> |
|--|-------------|
| 1. Exploded schematic view of experimental arrangement of test specimen pieces and heat-flux-generating foil..... | 3 |
| 2 Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M10 homogeneous single-base propellant..... | 10 |
| 3. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M9 homogeneous double-base propellant | 10 |
| 4. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for JA2 homogeneous triple-base propellant | 11 |
| 5. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M30 composite triple-base propellant, for heat flow in a direction <i>normal to the extrusion axis</i> | 11 |
| 6. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M30 composite triple-base propellant, for heat flow in a direction <i>parallel to the extrusion axis</i> | 12 |
| 7. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for XM39 composite nitramine propellant | 12 |
| 8. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M43 composite nitramine propellant | 13 |

INTENTIONALLY LEFT BLANK.

LIST OF TABLES

| <u>Table</u> | <u>Page</u> |
|--|-------------|
| 1. M10 Composition (Lot No. RAD-PE-792-85, Packed 5/90) | 5 |
| 2. M9 Composition (Lot No. RAD-PE-792-77, Packed 2/90) | 5 |
| 3. JA2 Composition (Lot No. RAD-PE-792-68, Packed 5/89) | 6 |
| 4. M30 Composition (Lot No. RAD-PE-792-82, Packed 2/90) | 6 |
| 5. XM39 Composition (Lot No. IH-XM39-0988-100 A1, Packed 9/88) | 7 |
| 6. M43 Composition (Lot No. IH-HELPI-0988-131 B1, Packed 9/88) | 7 |
| 7. $10^4 \times$ Thermal Conductivity (cal/cm-s- $^{\circ}$ C) | 9 |
| 8. $10^3 \times$ Thermal Diffusivity (cm ² /s) | 9 |
| 9. Polynomial Fits of Thermal Conductivity δ | 13 |
| 10. Polynomial Fits of Thermal Diffusivity " | 14 |
| 11. Polynomial Fits of Specific Heat c_p | 14 |

INTENTIONALLY LEFT BLANK.

1. INTRODUCTION

Thermal transport properties of unreacted solid propellants play an important role in determining how much of the chemical energy release is retained in the reaction zones and, in turn, the rate of combustion and surface regression. Notwithstanding this obvious relevance to combustion modeling as well as to calculations of ignition, cookoff, and environmental temperature accommodation, few measurements of these properties have been published for solid propellants in general. Moreover, we have been unable to find any published data at all for solid *gun* propellants in particular. This deficiency, in part, may be due to the experimental difficulties attending the measurement of transport properties using small test specimens. With gun propellants one is generally limited to specimens of linear dimensions on the order of half a cm, but small specimens are also desirable for explosives and rocket propellants from a safety standpoint. This report documents simultaneous measurements of thermal conductivity and thermal diffusivity of six solid gun propellants over the temperature range of -20°C to $+50^{\circ}\text{C}$ using a newly developed experimental technique appropriate for such small specimens (Miller and Kotlar, 1993). The propellants studied constitute the BRL Research-Series Propellants, a quantity of single-batch, standard Army gun propellants manufactured specifically for advanced combustion-mechanism research. This group of propellants includes examples of each different type of propellant formulation currently of interest: M10 (single base), M9 (homogeneous double base), JA2 (homogeneous triple base), M30 (composite triple base), and XM39 (composite nitramine). In addition to providing needed data for combustion-mechanism research on these particular materials, the data should enable rational estimates of the thermal transport properties to be made of other propellants with similar ingredients. Measurements of the specific heats of these same propellants over the temperature range -40°C to 75°C are reported elsewhere (Miller, 1992a). A table summarizing the polynomial fits to thermal diffusivity, thermal conductivity, and specific heat for all of these propellants is given at the end of this report. With the exception of M43, these data have also been published in the open literature (Miller (1994a), Miller (1994b)).

2. EXPERIMENTAL TECHNIQUE

The design of the experimental fixture and the data-reduction procedures are discussed and justified at length in a separate paper (Miller and Kotlar, 1993). Here we provide a short summary of the technique for coherence and completeness. In essence the experiment is designed to approximate closely the mathematical idealization of two one-dimensional semi-infinite solids separated by the plane $x = 0$, which is subjected to a step-function heat flux at $t = 0$. The exact solution to the heat-conduction equation for the temperature at some distance x from the source plane at some time t is given by Carslaw and Jaeger (1959),

$$T = T_0 + \left(\frac{2f_0\lambda\sqrt{\alpha_b}}{\lambda\sqrt{\alpha_b} + \lambda_b\sqrt{\alpha}} \right) \sqrt{\alpha t} \operatorname{ierfc} \left(\frac{x}{2\sqrt{\alpha t}} \right)$$

where the test material is assumed to occupy the region $x > 0$, the *base* material of known thermal properties occupies the region $x < 0$, α and α_b are the thermal diffusivities of the test material and the base respectively, λ and λ_b are the thermal conductivities of the test material and base, T_0 is the initial temperature everywhere at $t = 0$, and f_0 is the magnitude of the heat flux for $t > 0$.

Experimentally, the step-function heat flux is generated by the sudden application of a constant voltage to a thin resistance foil located at the interface of the two "semi-infinite" solids. If the current established in the foil is I , its electrical resistance R , its length L , and its width W , then the heat flux is given by

$$f_0 = \frac{I^2 R}{LW}$$

The ideality with which a step-function current in a foil can produce a step-function heat flux has been thoroughly discussed by Miller (1992b), who derived an exact Laplace-transform solution to the problem of a finite-thickness foil. The finite heat capacity of the foil delays the attainment of a constant heat flux even when the current in the foil is a perfect step function. This effect is minimized by using very thin foils. In the measurements reported here a Constantan foil 5- μm thick

is employed, resulting in errors in the thermal conductivities and diffusivities of less than 2% due to non-idealities in the step-function heat flux.




Figure 1. Exploded schematic view of experimental arrangement of test specimen pieces and heat-flux-generating foil.

Fig. 1 shows a schematic representation of the experimental setup. In reality, the foil is wider than the specimen diameter and thermal guards are employed. Voltage from a regulated DC supply is applied to the foil by means of a mercury-wetted relay. The temperature as a function of time (up to about 4 s) is then measured in the test specimen at a distance of about 0.5 mm from the foil by means of a 5- μ m-thick Chromel-Alumel foil-type thermocouple interposed between a test-specimen wafer and a test-specimen back-up piece. The back-up piece is about 0.65 cm long which is sufficiently long to give temperatures that differ from an infinitely thick piece by less than 1%. The many conditions for the experiment to closely approximate the mathematical idealization embodied in Eq. 1 are analyzed in detail by Miller and Kotlar (1993). A determination of the thermal

conductivity λ and diffusivity α is then made by performing a non-linear least-squares fit of Eq. 1 to the data using λ and α as fitting parameters. Temperature conditioning of the copper conductivity/diffusivity fixture was accomplished by means of ethylene glycol circulated from a temperature-controlled bath through copper tubing soldered to the fixture. A mineral-fiber insulation jacket thermally isolated the fixture from its environment.

3. PROPELLANT DESCRIPTIONS

All the tested propellants were extruded with a diameter close to 6.4 mm. Specimen wafers were cut to a thickness of about 0.5 mm with a low-speed, diamond-bladed wafering saw using water as a coolant. This saw produces smooth, low distortion cuts and wafers of very uniform thickness. After cutting, the specimens were placed in a desiccator for several days prior to experimentation. The compositions of the propellants are given in Tables 1 - 6 and are taken from manufacturer-supplied data sheets where it is customary to list the volatile components separately, presumably because of changes during storage. Test specimens from each lot were prepared by cutting the cylindrical strands perpendicular to the axis of extrusion. This results in heat flowing along or parallel to the extrusion axis. When M30 is extruded, the needle-like nitroguanidine crystals line up in the direction of extrusion. To see what effect this alignment might have on heat conduction, an M30 specimen was also prepared by cutting a specimen wafer and number of 1-mm-thick slabs parallel to the extrusion axis. The 1-mm-thick slabs were stacked to form a specimen back-up piece. Thermal contact resistance between these slabs had been found to be negligible by Miller and Kotlar (1993), a fact which justifies use of the composite specimen. Thus, the conductivity and diffusivity of M30 were measured in directions both parallel to and normal to the extrusion axis.

Table 1. M10 Composition (Lot No. RAD-PE-792-85, Packed 5/90)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|---------------------------|-----------------------|
| | (Actual) |
| Nitrocellulose (13.12% N) | 97.64 |
| Potassium Sulfate | 1.29 |
| Diphenylamine | 1.07 |
| TOTAL | 100.00 |
| (Total Volatiles) | (8.73) |

Table 2. M9 Composition (Lot No. RAD-PE-792-77, Packed 2/90)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|---------------------------|-----------------------|
| | (Actual) |
| Nitrocellulose (13.29% N) | 57.62 |
| Nitroglycerin | 40.02 |
| Ethyl Centralite | 0.73 |
| Potassium Nitrate | 1.63 |
| TOTAL | 100.00 |
| (Total Volatiles) | (0.26) |

Table 3. JA2 Composition (Lot No. RAD-PE-792-68, Packed 5/89)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|-----------------------------|-----------------------|
| | (Actual) |
| Nitrocellulose (13.04% N) | 58.21 |
| Nitroglycerin | 15.79 |
| Diethylene Glycol Dinitrate | 25.18 |
| Akardit II | 0.74 |
| Magnesium Oxide | 0.05 |
| Graphite | 0.03 |
| TOTAL | 100.00 |
| (Moisture Content) | (0.34) |

Table 4. M30 Composition (Lot No. RAD-PE-792-82, Packed 2/90)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|---------------------------|-----------------------|
| | (Actual) |
| Nitrocellulose (12.68% N) | 28.71 |
| Nitroglycerin | 22.02 |
| Nitroguanidine | 47.34 |
| Ethyl Centralite | 1.58 |
| Cryolite | 0.35 |
| TOTAL | 100.00 |
| (Total Volatiles) | (0.67) |

Table 5. XM39 Composition (Lot No. IH-XM39-0988-100 A1, Packed 9/88)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|----------------------------|-----------------------|
| | (Nominal) |
| RDX (5 micron) | 76.0 |
| Cellulose Acetate Butyrate | 12.0 |
| Nitrocellulose (12.6% N) | 4.0 |
| Acetyl Triethyl Citrate | 7.6 |
| Ethyl Centralite | 0.4 |
| TOTAL | 100.0 |
| (Total Volatiles) | (0.14) |

Table 6. M43 Composition (Lot No. IH-HELP1-0988-131 B1, Packed 9/88)

| <u>CONSTITUENT</u> | <u>WEIGHT PERCENT</u> |
|----------------------------|-----------------------|
| | (Nominal) |
| RDX (5 micron) | 76.0 |
| Cellulose Acetate Butyrate | 12.0 |
| Nitrocellulose (12.6% N) | 4.0 |
| Energetic Plasticizer | 7.6 |
| Ethyl Centralite | 0.4 |
| TOTAL | 100.0 |
| (Total Volatiles) | (not available) |

4. RESULTS

For each propellant at each different temperature, five runs were averaged to obtain the best value of conductivity and diffusivity at that temperature. The average values along with their standard deviations are given in Tables 7 and 8. Parabolic least-squares fits to these data are shown along with the data in Figs. 2 - 7, and the fitting parameters are collected in Tables 9 - 10. Error bars shown in the figures are the 5-run standard deviations. For M30, heat transfer along the extrusion axis proved to be about one third faster than in a direction normal to the extrusion axis, no doubt due to conduction enhancement afforded by alignment of the needle-like nitroguanidine crystals parallel to the extrusion axis. The microstructure of the other propellants is nearly isotropic so the conductivities are presumed to be isotropic. For this reason no subscript is used to denote direction for samples other than M30, even though measurements were made only along the extrusion axis. By comparing the values for thermal conductivity and diffusivity measured with the present technique to literature values for polymethylmethacrylate and Pyrex, Miller and Kotlar (1993) estimated that the technique provides an accuracy of $\pm 5\%$ for materials with properties between these standards. The results reported here all satisfy this condition.

For convenience the polynomial fits to previously reported measurements (Miller (1992a)) of specific heats of specimens from the same six lots are given in Table 11. Estimated accuracy for these data is also $\pm 5\%$.

| TABLE 7. $10^4 \times$ Thermal Conductivity (cal/cm-s-°C) | | | | | | |
|---|-------------|-------------|-------------|------------------|-------------------|-------------|
| (⊥ indicates normal to extrusion axis, // indicates parallel to extrusion axis) | | | | | | |
| Temperature | M10 | M9 | JA2 | M30 _⊥ | M30 _{//} | XM39 |
| - 19°C | 6.66 ± 0.34 | no data | 7.06 ± 0.59 | no data | 10.0 ± 0.5 | 6.12 ± 0.25 |
| - 18°C | no data | 6.61 ± 0.41 | no data | 7.87 ± 0.16 | no data | no data |
| 2°C | no data | no data | no data | 8.41 ± 0.23 | no data | no data |
| 3°C | 7.36 ± 0.27 | 7.06 ± 0.34 | 6.98 ± 0.50 | no data | 11.6 ± 0.7 | 6.34 ± 0.27 |
| 22°C | no data | no data | 6.94 ± 0.29 | no data | 10.2 ± 0.6 | 5.86 ± 0.20 |
| 23°C | 7.50 ± 0.28 | 7.08 ± 0.22 | no data | no data | 10.7 ± 0.6 | no data |
| 24°C | no data | no data | no data | 7.64 ± 0.80 | no data | no data |
| 48°C | 7.26 ± 0.35 | no data | no data | 7.76 ± 0.52 | no data | 5.88 ± 0.24 |
| 49°C | no data | 6.92 ± 0.15 | 6.70 ± 0.27 | no data | 9.84 ± 0.38 | no data |

| TABLE 8. $10^3 \times$ Thermal Diffusivity (cm ² /s) | | | | | | |
|---|-------------|-------------|-------------|------------------|-------------------|-------------|
| (⊥ indicates normal to extrusion axis, // indicates parallel to extrusion axis) | | | | | | |
| Temperature | M10 | M9 | JA2 | M30 _⊥ | M30 _{//} | XM39 |
| - 19°C | 1.79 ± 0.07 | no data | 1.62 ± 0.11 | no data | 2.34 ± 0.09 | 1.54 ± 0.03 |
| - 18°C | no data | 1.49 ± 0.07 | no data | 1.78 ± 0.03 | no data | no data |
| 2°C | no data | no data | no data | 1.74 ± 0.04 | no data | no data |
| 3°C | 1.81 ± 0.05 | 1.44 ± 0.07 | 1.45 ± 0.08 | no data | 2.41 ± 0.14 | 1.50 ± 0.04 |
| 22°C | no data | no data | 1.30 ± 0.05 | no data | 1.90 ± 0.09 | 1.32 ± 0.04 |
| 23°C | 1.79 ± 0.04 | 1.33 ± 0.03 | no data | no data | 2.09 ± 0.11 | no data |
| 24°C | no data | no data | no data | 1.46 ± 0.11 | no data | no data |
| 48°C | 1.55 ± 0.05 | no data | no data | 1.39 ± 0.08 | no data | 1.21 ± 0.04 |
| 49°C | no data | 1.31 ± 0.03 | 1.30 ± 0.03 | no data | 1.88 ± 0.04 | no data |




Figure 2. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M10 homogeneous single-base propellant.




Figure 3. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M9 homogeneous double-base propellant.




Figure 4. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for JA2 homogeneous triple-base propellant.




Figure 5. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M30 composite triple-base propellant, for heat flow in a direction *normal to the extrusion axis*.




Figure 6. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M30 composite triple-base propellant, for heat flow in a direction *parallel to the extrusion axis*.




Figure 7. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for XM39 composite nitramine propellant.




Figure 8. Thermal conductivity data (open circles, right scale), thermal diffusivity (solid circles, left scale), and their least-squares second-degree polynomial fits (line) for M43 composite nitramine propellant.

TABLE 9. Polynomial Fits of Thermal Conductivity λ

(LEAST-SQUARES FITS)

$$\lambda(\text{cal/cm-s-}^{\circ}\text{C}) = f_0 + f_1T + f_2T^2, \text{ for } T \text{ in } (-20, +50^{\circ}\text{C})$$

(\perp indicates normal to extrusion axis, // indicates parallel to extrusion axis)

| Coefficient | M10 | M9 | JA2 | M30 \perp | M30 $//$ | XM39 | M43 |
|-------------|-----------|-----------|-----------|-------------|-----------|----------|-----------|
| f_0 | 7.263E-4 | 6.971E-4 | 7.012E-4 | 8.058E-4 | 1.082E-3 | 6.147E-4 | 6.011E-4 |
| f_1 | 2.243E-6 | 1.357E-6 | -3.064E-7 | 1.827E-8 | 1.461E-6 | 3.080E-7 | 2.146E-8 |
| f_2 | -4.716E-8 | -3.017E-8 | -6.363E-9 | -1.756E-8 | -7.766E-8 | 7.351E-9 | -1.669E-8 |

TABLE 10. Polynomial Fits of Thermal Diffusivity α

(LEAST-SQUARES FITS)

$$\alpha(\text{cm}^2/\text{s}) = f_0 + f_1T + f_2T^2, \text{ for } T \text{ in } (-20, +50^\circ\text{C})$$

(\perp indicates normal to extrusion axis, // indicates parallel to extrusion axis)

| Coefficient | M10 | M9 | JA2 | M30 \perp | M30 $//$ | XM39 | M43 |
|-------------|-----------|-----------|-----------|-------------|-----------|-----------|-----------|
| f_0 | 1.831E-3 | 1.426E-3 | 1.447E-3 | 1.683E-3 | 2.252E-3 | 1.470E-3 | 1.387E-3 |
| f_1 | 1.218E-7 | -3.449E-6 | -7.491E-6 | -6.790E-6 | -7.603E-6 | -4.781E-6 | -4.605E-6 |
| f_2 | -1.207E-7 | 2.003E-8 | 9.095E-8 | 3.323E-9 | -1.722E-8 | -1.979E-8 | 1.124E-8 |

TABLE 11. Polynomial Fits of Specific Heat c_p

(LEAST-SQUARES FITS)

$$c_p(\text{cal/g-}^\circ\text{C}) = f_0 + f_1T + f_2T^2 + f_3T^3 + f_4T^4, \text{ for } T \text{ in } (-40, +75^\circ\text{C})$$

| Coefficient | M10 | M9 | JA2 | M30 | XM39 | M43 |
|-------------|------------|-----------|-----------|-----------|------------|------------|
| f_0 | 2.404E-1 | 2.987E-1 | 3.003E-1 | 2.887E-1 | 2.496E-1 | 2.487E-1 |
| f_1 | 7.831E-4 | 7.728E-4 | 8.128E-4 | 8.434E-4 | 7.25E-4 | 7.639E-4 |
| f_2 | 3.821E-6 | 1.031E-6 | 1.057E-6 | 4.800E-7 | 1.575E-6 | 4.105E-7 |
| f_3 | 5.201E-8 | 1.700E-7 | 1.552E-7 | 1.017E-7 | 6.144E-8 | 4.129E-8 |
| f_4 | -9.439E-10 | -2.278E-9 | -2.190E-9 | -1.537E-9 | -9.142E-10 | -5.334E-10 |

5. CONCLUSIONS

Thermophysical properties are required for a wide range of ignition and combustion calculations and yet few measurements of these properties have been published for solid propellants. This report documents such measurements for six U. S. Army solid gun propellants over the temperature range -20°C to $+50^{\circ}\text{C}$ using a newly developed technique for the simultaneous determination of thermal conductivity and diffusivity of small test specimens. The accuracy of these measurements, including previously measured specific heats, is estimated to be $\pm 5\%$ and least-squares polynomial fits of these data are provided as a function of temperature for convenience in calculations.

INTENTIONALLY LEFT BLANK.

REFERENCES

Carslaw and Jaeger, Conduction of Heat in Solids, 2nd Ed., Oxford University Press, London, p. 88, 1959.

Miller, Martin S., "Specific-Heat Measurements for Gun Propellants", BRL Technical Report BRL-TR-3378, Ballistic Research Laboratory, Aberdeen Proving Ground, MD, July 1992a.

Miller, Martin S., "Step-Function Current in a Metallic Foil as a Step-Function Heat-Flux Source", J. Appl. Phys. **72**, pp. 3904 - 3907, 1992b.

Miller, M. S. and Kotlar, A. J., "Technique for Measuring Thermal Diffusivity/Conductivity of Small Thermal-Insulator Specimens", Review of Scientific Instruments, Vol. 64, pp. 2954 - 2960, 1993.

Miller, Martin S., "Thermal Conductivities and Diffusivities of Solid Gun Propellants," Combust. Sci. and Tech., Vol. 100, pp. 345 - 354, 1994a.

Miller, Martin S., "Specific Heats of Solid Gun Propellants," Combust. Sci. and Tech., Vol. 102, pp. 273 - 281, 1994b.

INTENTIONALLY LEFT BLANK.

| <u>NO. OF COPIES</u> | <u>ORGANIZATION</u> |
|--------------------------------|--|
| 2 | DEFENSE TECHNICAL INFO CTR ATTN DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218 |
| 1 | HQDA DAMO FDQ ATTN DENNIS SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460 |
| 1 | US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI ATTN MDN A MAJ DON ENGEN THAYER HALL WEST POINT NY 10996-1786 |
| 1 | DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TP 2800 POWDER MILL RD ADELPHI MD 20783-1145 |
| 1 | DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TA 2800 POWDER MILL RD ADELPHI MD 20783-1145 |
| 3 | DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1145 |
| <u>ABERDEEN PROVING GROUND</u> | |
| 2 | DIR USARL ATTN AMSRL CI LP (305) |

| NO. OF COPIES | ORGANIZATION |
|------------------|--|
| 4 | NATIONAL BUREAU OF STANDARDS US DEPARTMENT OF COMMERCE ATTN J HASTIE M JACOX T KASHIWAGI H SEMERJIAN WASHINGTON DC 20234 |
| 1 | OSD/SDIO/IST ATTN L CAVENY PENTAGON WASHINGTON DC 20301-7100 |
| 2 | HQDA SARD TT DR F MILTON MR J APPEL WASH DC 20310-0103 |
| 1 | HQDA OASA RDA ATTN DR C H CHURCH PENTAGON ROOM 3E486 WASH DC 20310-0103 |
| 5 | CDR ARO ATTN R GHIRARDELLI D MANN R SINGLETON R SHAW AMXRO RT IP LIBRARY SERVICES PO BOX 12211 RSCH TRIANGLE PARK NC 27709-2211 |
| 3 | CDR ARDEC ATTN SMCAR AEE B D S DOWNS SMCAR AEE BR L HARRIS SMCAR AEE J A LANNON PICATINNY ARSENAL NJ 07806-5000 |
| 1 | DIRECTOR US ARMY BENET LABORATORY ATTN SMCAR CCB B SAM SOPOK WATERVALIET NY 12189 |
| 2 | CDR MICOM ATTN AMSMI RD PR E A R MAYKUT AMSMI RD PR P R BETTS REDSTONE ARSENAL AL 35898-5000 |
| 1 | OFFICE OF NAVAL RESEARCH DEPARTMENT OF THE NAVY ATTN R S MILLER CODE 432 800 N QUINCY STREET ARLINGTON, VA 22217 |

| NO. OF COPIES | ORGANIZATION |
|------------------|--|
| 1 | CDR NAVAL AIR SYSTEMS CMD ATTN J RAMNARACE AIR-54111C WASHINGTON DC 20360 |
| 2 | CDR NAVAL SURFACE WARFARE CTR ATTN R BERNECKER R-13 G B WILMOT R-16 SILVER SPRING MD 20903-5000 |
| 5 | CDR NAVAL RESEARCH LABORATORY ATTN M C LIN J MCDONALD E ORAN J SHNUR R J DOYLE CODE 6110 WASHINGTON DC 20375 |
| 2 | CDR NAVAL WEAPONS CTR ATTN T BOGGS CODE 388 T PARR CODE 3895 CHINA LAKE CA 93555-6001 |
| 1 | SUPERINTENDENT NAVAL POSTGRADUATE SCHOOL DEPT OF AERONAUTICS ATTN D W NETZER MONTEREY CA 93940 |
| 3 | AL/LSCF ATTN R CORLEY R GEISLER J LEVINE EDWARDS AFB CA 93523-5000 |
| 1 | AFOSR ATTN J M TISHKOFF BOLLING AFB WASHINGTON DC 20332 |
| 1 | CMDT USAFAS ATTN ATSF TSM CN FORT SILL OK 73503-5600 |
| 1 | UNIV OF DAYTON RSCH INSTITUTE ATTN D CAMPBELL AL/PAP EDWARDS AFB CA 93523 |
| 1 | NASA LANGLEY RESEARCH CENTER LANGLEY STATION ATTN G B NORTHAM MS 168 HAMPTON VA 23365 |

| NO. OF COPIES | ORGANIZATION |
|------------------|---|
| 1 | DIR LANL ATTN B NICHOLS T7 MS-B284 PO BOX 1663 LOS ALAMOS NM 87545 |
| 2 | DIR LLNL ATTN C WESTBROOK W TAO MS L282 PO BOX 808 LIVERMORE CA 94550 |
| 3 | DIR SNL DIVISION 8354 ATTN S JOHNSTON P MATTERN D STEPHENSON LIVERMORE CA 94550 |
| 1 | BRIGHAM YOUNG UNIV DEPT OF CHEMICAL ENGINEERING ATTN M W BECKSTEAD PROVO UT 84058 |
| 1 | CA INSTITUTE OF TECHNOLOGY JET PROPULSION LABORATORY ATTN L STRAND MS 125-224 4800 OAK GROVE DRIVE PASADENA CA 91109 |
| 1 | CA INSTITUTE OF TECHNOLOGY ATTN F E C CULICK MC 301-46 204 KARMAN LAB PASADENA CA 91125 |
| 1 | CORNELL UNIV DEPARTMENT OF CHEMISTRY ATTN T A COOL BAKER LABORATORY ITHACA NY 14853 |
| 3 | GA INST OF TECHNOLOGY SCHOOL OF AEROSPACE ENGINEERING ATTN E PRICE W C STRAHLE B T ZINN ATLANTA GA 30332 |
| 1 | THE JOHNS HOPKINS UNIV CHEMICAL PROPULSION INFO AGENCY ATTN T W CHRISTIAN 10630 LITTLE PATUXENT PKWY STE 202 COLUMBIA MD 21044-3200 |

| NO. OF COPIES | ORGANIZATION |
|------------------|--|
| 4 | PENNSYLVANIA STATE UNIV DEPT OF MECHANICAL ENGINEERING ATTN K KUO M MICCI S THYNELL V YANG UNIVERSITY PARK PA 16802 |
| 2 | PRINCETON UNIVERSITY FORRESTAL CAMPUS LIBRARY ATTN K BREZINSKY I GLASSMAN PO BOX 710 PRINCETON NJ 08540 |
| 1 | PURDUE UNIVERSITY SCHOOL OF AERONAUTICS & ASTRONAUTICS ATTN J R OSBORN GRISSOM HALL WEST LAFAYETTE IN 47906 |
| 1 | PURDUE UNIVERSITY DEPT OF CHEMISTRY ATTN E GRANT WEST LAFAYETTE, IN 47906 |
| 2 | PURDUE UNIVERSITY SCHOOL OF MECH ENGINEERING ATTN N M LAURENDEAU S N B MURTHY TSPC CHAFFEE HALL WEST LAFAYETTE IN 47906 |
| 1 | RENSSELAER POLYTECHNIC INST DEPT OF CHEMICAL ENGINEERING ATTN A FONTIJN TROY NY 12181 |
| 1 | STANFORD UNIVERSITY DEPT OF MECH ENGINEERING ATTN R HANSON STANFORD CA 94305 |
| 1 | UNIV OF CALIFORNIA LOS ALAMOS SCIENTIFIC LAB PO BOX 1663 MS B216 LOS ALAMOS NM 87545 |
| 1 | UNIV OF CA-BERKELEY CHEMISTRY DEPARMENT ATTN C BRADLEY MOORE 211 LEWIS HALL BERKELEY CA 94720 |

| <u>NO. OF COPIES</u> | <u>ORGANIZATION</u> | <u>NO. OF COPIES</u> | <u>ORGANIZATION</u> |
|--------------------------|---|--------------------------|--|
| 1 | UNIV OF CA SAN DIEGO ATTN F A WILLIAMS AMES B010 LA JOLLA CA 92093 | 1 | UNIVERSITY OF TEXAS DEPT OF CHEMISTRY ATTN W GARDINER AUSTIN TX 78712 |
| 2 | UNIV OF CA SANTA BARBARA QUANTUM INSTITUTE ATTN K SCHOFIELD M STEINBERG SANTA BARBARA CA 93106 | 1 | VA POLYTECHNIC INST & STATE UNIV ATTN J A SCHETZ BLACKSBURG VA 24061 |
| 1 | UNIV OF CO AT BOULDER ENGINEERING CENTER ATTN J DAILY CAMPUS BOX 427 BOULDER CO 80309-0427 | 8 | ALLIANT TECHSYSTEMS INC MARINE SYSTEMS GROUP ATTN R BECKER J BODE D E BRODEN MS MN50-2000 R BURETTA C CANDLAND L OSGOOD M SWENSON R E TOMPKINS MN11-2720 600 2ND STREET NE HOPKINS MN 55343 |
| 1 | UNIV OF DELAWARE ATTN T BRILL CHEMISTRY DEPARTMENT NEWARK DE 19711 | 1 | APPLIED COMBUSTION TECH INC ATTN A M VARNEY PO BOX 607885 ORLANDO FL 32860 |
| 1 | UNIV OF FLORIDA DEPT OF CHEMISTRY ATTN J WINEFORDNER GAINESVILLE FL 32611 | 2 | APPLIED MECHANICS REVIEWS THE AMERICAN SOCIETY OF MECH ENGINEERS ATTN R E WHITE A B WENZEL 345 E 47TH STREET NEW YORK NY 10017 |
| 1 | UNIV OF ILLINOIS DEPT OF MECH ENG ATTN H KRIER 144MEB 1206 W GREEN ST URBANA IL 61801 | 1 | BATTELLE TWSTIAC HUGGINS 505 KING AVENUE COLUMBUS OH 43201-2693 |
| 1 | UNIV OF MICHIGAN GAS DYNAMICS LAB AEROSPACE ENGINEERING BLDG ATTN G M FAETH ANN ARBOR MI 48109-2140 | 1 | COHEN PROFESSIONAL SERVICES ATTN N S COHEN 141 CHANNING STREET REDLANDS CA 92373 |
| 1 | UNIV OF MINNESOTA DEPT OF MECH ENGINEERING ATTN E FLETCHER MINNEAPOLIS MN 55455 | 1 | EXXON RESEARCH & ENG CO ATTN A DEAN ROUTE 22E ANNANDALE NJ 08801 |
| 3 | UNIV OF SOUTHERN CA DEPT OF CHEMISTRY ATTN R BEAUDET S BENSON C WITTIG LOS ANGELES CA 90007 | 1 | FREEDMAN ASSOCIATES ATTN E FREEDMAN 2411 DIANA ROAD BALTIMORE MD 21209-1525 |

NO. OF
COPIES ORGANIZATION

1 GE ORDNANCE SYSTEMS
ATTN J MANDZY
100 PLASTICS AVENUE
PITTSFIELD MA 01203

1 GENERAL APPLIED SCIENCE LABS INC
77 RAYNOR AVENUE
RONKONKAMA NY 11779-6649

1 GENERAL MOTORS RSCH LABS
PHYSICAL CHEMISTRY DEPARTMENT
ATTN T SLOANE
WARREN MI 48090-9055

2 HERCULES INC
ALLEGHENY BALLISTICS LAB
ATTN W B WALKUP
E A YOUNT
PO BOX 210
ROCKET CENTER WV 26726

1 HERCULES INC
ATTN R V CARTWRIGHT
100 HOWARD BLVD
KENVIL NJ 07847

1 HUGHES AIRCRAFT COMPANY
ATTN T E WARD
8433 FALLBROOK AVENUE
CANOGA PARK CA 91303

1 IBM CORPORATION
RESEARCH DIVISION
ATTN A C TAM
5600 COTTLE ROAD
SAN JOSE CA 95193

1 IIT RESEARCH INSTITUTE
ATTN R F REMALY
10 WEST 35TH STREET
CHICAGO IL 60616

1 LOCKHEED MISSILES & SPACE CO
DEPT 52-35 B204 2
ATTN GEORGE LO
3251 HANOVER STREET
PALO ALTO CA 94304

1 OLIN ORDNANCE
ATTN V MCDONALD LIBRARY
PO BOX 222
ST MARKS FL 32355-0222

NO. OF
COPIES ORGANIZATION

1 PAUL GOUGH ASSOCIATES INC
ATTN P S GOUGH
1048 SOUTH STREET
PORTSMOUTH NH 03801-5423

2 PRINCETON COMB RSCH LABS INC
ATTN N A MESSINA
M SUMMERFIELD
PRINCETON CORPORATE PLAZA
BLDG IV SUITE 119
11 DEERPARK DRIVE
MONMOUTH JUNCTION NJ 08852

1 ROCKWELL INTERNATIONAL CORP
ROCKETDYNE DIVISION
ATTN J E FLANAGAN HB02
6633 CANOGA AVENUE
CANOGA PARK CA 91304

1 SCIENCE APPLICATIONS INC
ATTN R B EDELMAN
23146 CUMORAH CREST
WOODLAND HILLS CA 91364

3 SRI INTERNATIONAL
ATTN G SMITH
D CROSLEY
D GOLDEN
333 RAVENSWOOD AVENUE
MENLO PARK CA 94025

1 STEVENS INSTITUTE OF TECH
DAVIDSON LABORATORY
ATTN R MCALEVY III
HOBOKEN NJ 07030

2 SVERDRUP TECHNOLOGY INC
LERC GROUP
ATTN R J LOCKE MS SVR-2
J DEUR
2001 AEROSPACE PARKWAY
BROOK PARK OH 44142

1 TEXTRON DEFENSE SYSTEMS
ATTN A PATRICK
2385 REVERE BEACH PARKWAY
EVERETT MA 02149-5900

| <u>NO. OF COPIES</u> | <u>ORGANIZATION</u> |
|--------------------------|--|
| 3 | THIOKOL CORPORATION ELKTON DIVISION ATTN R BIDDLE R WILLER TECH LIB PO BOX 241 ELKTON MD 21921 |
| 3 | THIOKOL CORPORATION WASATCH DIVISION ATTN S J BENNETT PO BOX 524 BRIGHAM CITY UT 84302 |
| 1 | UNITED TECHNOLOGIES CORP CHEMICAL SYSTEMS DIVISION ATTN R R MILLER PO BOX 49028 SAN JOSE CA 95161-9028 |
| 1 | UNITED TECHNOLOGIES RSCH CTR ATTN A C ECKBRETH EAST HARTFORD CT 06108 |
| 1 | UNIVERSAL PROPULSION COMPANY ATTN H J MCSPADDEN 25401 NORTH CENTRAL AVENUE PHOENIX AZ 85027-7837 |
| 1 | VERITAY TECHNOLOGY INC ATTN E B FISHER 4845 MILLERSPORT HIGHWAY PO BOX 305 EAST AMHERST NY 14051-0305 |

| <u>NO. OF COPIES</u> | <u>ORGANIZATION</u> |
|--------------------------|--|
| | <u>ABERDEEN PROVING GROUND</u> |
| 41 | DIR USARL ATTN AMSRL W M P G F ADAMS W R ANDERSON R A BEYER K P MC-NEILL BOONSTOPPEL S W BUNTE C F CHABALOWSKI A COHEN R CUMPTON R DANIEL D DEVYNCK R A FIFER B E FORCH J M HEIMERL B E HOMAN A W HORST A JUHASZ A J KOTLAR R KRANZE E LANCASTER W F MCBRATNEY K L MCNESBY M MCQUAID N E MEAGHER M S MILLER A W MIZIOLEK J B MORRIS J E NEWBERRY S V PAI R A PESCE-RODRIGUEZ J RASIMAS P REEVES B M RICE P SAEGAR R C SAUSA M A SCHROEDER R SCHWEITZER L D SEGER J A VANDERHOFF D VENIZELOS A WHREN H L WILLIAMS |

| REPORT DOCUMENTATION PAGE | | | Form Approved OMB No. 0704-0188 | |
|---|---|---|--|--|
| Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503. | | | | |
| 1. AGENCY USE ONLY (Leave blank) | 2. REPORT DATE March 1997 | 3. REPORT TYPE AND DATES COVERED Final, 15 Jan 92 - 1 Jun 93 | | |
| 4. TITLE AND SUBTITLE Thermophysical Properties of Six Solid Gun Propellants | | | 5. FUNDING NUMBERS PR: 1L161102AH43 | |
| 6. AUTHOR(S) Martin S. Miller | | | | |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-PC Aberdeen Proving Ground, MD 21005-5066 | | | 8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1322 | |
| 9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES) | | | 10. SPONSORING/MONITORING AGENCY REPORT NUMBER | |
| 11. SUPPLEMENTARY NOTES Most of the data in this report were published in two open literature papers: Martin S. Miller, Combustion Science and Technology, vol. 100, pp. 345-354, 1994, and vol. 102, pp. 273-281, 1994. | | | | |
| 12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited. | | | 12b. DISTRIBUTION CODE | |
| 13. ABSTRACT (Maximum 200 words) Measurements are reported of the thermal conductivities and thermal diffusivities of six U.S. Army solid gun propellants over the temperature range -20°C to +50°C at atmospheric pressure. The propellants are members of the BRL research series propellants that have been widely distributed to research laboratories in the U.S. These propellants include representative types from each class of materials that are either in the fielded inventory or experimental ("X" prefix), i.e., a single base (M10), a double base (M9), a homogeneous triple base (JA2), a composite triple base (M30), a composite nitramine with inert plasticizer (XM39), and a composite nitramine with energetic plasticizer (M43). Conductivities and diffusivities were measured simultaneously using a new experimental technique developed specifically for the purpose. The experiment is designed to approximate the mathematical idealization of a one-dimensional, infinite, two-component, composite solid whose planar interface is subjected to a step-function heat flux. The average values obtained are estimated to be accurate to within $\pm 5\%$, and least-squares polynomial fits are provided for convenient use of the data in calculations. For convenience, a table is given summarizing the polynomial fits from the present measurements and from previous measurements of the specific heats for the same propellant lots. | | | | |
| 14. SUBJECT TERMS thermal conductivity, thermal diffusivity, specific heat, solid propellant, gun propellant | | | 15. NUMBER OF PAGES 28 | |
| | | | 16. PRICE CODE | |
| 17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED | 18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED | 19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED | 20. LIMITATION OF ABSTRACT UL | |

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1322 (Miller) Date of Report March 1997
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)

DEPARTMENT OF THE ARMY


OFFICIAL BUSINESS

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR
US ARMY RESEARCH LABORATORY
ATTN AMSRL WM PC
ABERDEEN PROVING GROUND MD 21005-5066



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

